

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) Publication number:

0 473 176 A2

(12)

EUROPEAN PATENT APPLICATION(21) Application number: **91114601.7**(51) Int. Cl.⁵: **C08L 23/04, C08L 29/04,
C08L 51/06**(22) Date of filing: **30.08.91**(30) Priority: **30.08.90 JP 226652/90**(43) Date of publication of application:
04.03.92 Bulletin 92/10(84) Designated Contracting States:
AT BE CH DE ES FR GB IT LI NL(71) Applicant: **KANSAI TUBE CO., LTD.**
5-8, Higashi 3-chome, Tamagushicho
Higashiosaka-shi, Osaka(JP)(72) Inventor: **Nishikawa, Kazuo**
101-9, Numa 1-chome
Yao-shi, Osaka(JP)(74) Representative: **Sandmair, Kurt, Dr. Dr. et al**
Patentanwälte Schwabe, Sandmair, Marx
Stuntzstrasse 16
W-8000 München 80(DE)(54) **Laminate-tube container improved in barrier property at shoulder thereof.**

(57) Disclosed is a laminate-tube container having a shoulder improved in the barrier property, which is characterized in that the shoulder comprises a material composed of (A) 0 to 50% by weight of polyethylene, (B) 10 to 50% by weight of an ethylene-vinyl alcohol copolymer or a saponified ethylene-vinyl acetate copolymer and (c) 10 to 90% by weight of a carboxylic acid-modified adhesive polyethylene resin. The laminate-tube can be markedly improved in the gas barrier property at the shoulder thereof and, thus, the quality of the contents of the container can be maintained for a long period of time. The laminate-tube container according to the present invention is greatly useful as the container to be used for toothpaste, medicine, food, drink, adhesive or the like.

EP 0 473 176 A2

BACKGROUND OF THE INVENTION

1. Field of the Invention

5 The present invention relates to a laminate-tube container to be used for toothpaste, food, cosmetic, medicine, adhesive or the like.

2. Description of the Prior Art

10 As a container to be used for toothpaste, food, cosmetic, medicine, adhesive or the like, a laminate-tube type container is available (refer to FIG. 1). The body of such a container is given a barrier property by an aluminum foil or an ethylene-vinyl alcohol copolymer, etc. However, since the shoulder (part A of FIG. 1) formed in the discharge side of the container is usually constituted of a material comprising a single resin such as polyethylene and is poor in gas barrier property, there have arisen various problems such that the
15 contents of the container, such as perfume, are released through the shoulder, while gases contained in the outer atmosphere, such as oxygen, enter the container through the shoulder, thus changing the quality of the contents.

In order to cope with these problems, there are available several methods, for example, a method in which a laminate-tube container is fitted with a doughnut-shaped member containing an aluminum foil at the
20 inside or outside of the shoulder of the container (rondelle type as shown in FIG. 2), a method in which a container is equipped with a cup-shaped member extending from the shoulder to the inside of the opening of the container (membrane rondelle type as shown in FIG. 3), or a method in which a preformed member of a resin having a high barrier property, such as polybutylene terephthalate (PBT), is installed on the container.

25 However, the practical use of these methods is hampered by a decrease in productivity, for example, with an increase in the number of processing steps, resulting in a high production cost.

SUMMARY OF THE INVENTION

30 In view of the above, it is an object of the present invention to provide a laminate-tube container improved in the barrier property at the shoulder thereof by utilizing the conventional laminate tube production process as such.

In order to solve the foregoing problem, the present inventors have intensively investigated a variety of shoulder materials for, a laminate-tube container and finally accomplished the present invention on the basis
35 of the finding that a specific resin blend is effective as a shoulder material for the container.

Namely the present invention relates to a laminate-tube container having a shoulder improved in the barrier property, which is characterized in that the shoulder comprises a material composed of (A) 0 to 50% by weight of polyethylene, (B) 10 to 50% by weight of an ethylene-vinyl alcohol copolymer or a saponified ethylene-vinyl acetate copolymer and (c) 10 to 90% by weight of a carboxylic acid-modified adhesive
40 polyethylene resin.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 is a schematic view of a laminate-tube container of the present invention.

45 FIG. 2 and FIG. 3 are each a schematic view of a conventional laminate-tube container.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

Now a description will be given to resin materials for a laminate-tube shoulder to be used in the present
50 invention.

The shoulder of a laminate-tube container according to the present invention is formed from a melt-blended resin composition comprising (A) polyethylene, (B) an ethylene-vinyl alcohol copolymer or a saponified ethylene-vinyl acetate copolymer and (C) a carboxylic acid-modified adhesive polyethylene resin.

A composition composed of the components A and B only is poor in the miscibility of the components
55 A and B, cannot give a homogeneous dispersion and fails in achieving a sufficient improvement in the gas barrier property.

As (A) polyethylene, there are available high-density polyethylene (HDPE), medium-density polyethylene, low-density polyethylene and linear low-density polyethylene (LLDPE), among which high-density

polyethylene is preferable.

In regard to (B) the ethylene-vinyl alcohol copolymer or saponified ethylene-vinyl acetate copolymer, the gas barrier property increases with a decrease in the ethylene comonomer content (mol %) in the copolymer. However, a decrease in this content causes insufficient adhesion and a decrease in the flexural strength when the shoulder and body of a laminate tube are adhesion-molded by compression molding. In view of the above, a copolymer with an ethylene comonomer content of 32 mol % is used in the Example as hereinafter described.

With respect to component (C), modification with a carboxylic acid is preferably effected with maleic anhydride. Specifically, a commercially available product sold under the tradename of Modic (a product of Mitsubishi Petrochemical Co., Ltd.), Admer (a product of Mitsui Petrochemical Industries Ltd.) or the like can be used as the component (C) of the present invention.

The compounding ratio by weight of the components (A), (B) and (C) is 0 to 50 : 10 to 50 : 10 to 90, preferably 0 to 50 : 30 to 50 : 30 to 50 taking into consideration the moldability of the resin composition.

A laminate-tube container according to the present invention can be greatly improved in the gas barrier property as compared with the conventional products by the shoulder composed of a resin composition comprising the above-mentioned components (A), (B) and (C).

It is important in the laminate-tube container according to the present invention that the material as selected above be used in the shoulder thereof. On the other hand, other parts of the container than the shoulder thereof may be composed of any conventional material, and also the conventional production process may be applied to the container of the present invention. It goes without saying that the whole of a tube container may be constituted of the melt-blended material comprising the aforementioned components (A), (B) and (C).

The present invention will now be described in more detail by referring to the following Example.

EXAMPLE

Three types of laminate-tube containers different in shoulder material from each other were produced.

In order to evaluate the gas barrier property of each of the containers, the oxygen permeation rate of each of the container was determined. The results are given in the Table.

Table

		<u>Comp. Ex.</u>	<u>Ex. 1</u>	<u>Ex. 2</u>
Composition	(A)	100	20	20
	(B)		30	40
	(% by weight) (C)		50	40
Oxygen permeation		0.267		
			0.0475	0.0300
<u>rate (cc/pkg.day.atm)</u>		<u>0.3215</u>		

Note: (A) HDPE (high-density polyethylene)
 (B) Eval (tradename of Kuraray Co., Ltd.)
 (C) MODIC (tradename of Mitsubishi Petrochemical Co., Ltd.)

As obvious from the above Table, the laminate tube having the shoulder constituted of the resin composition based on the three foregoing specific components according to the present invention exhibits an oxygen barrier performance of approximately 6 to 10 times that of the conventional laminate tube.

As described hereinbefore, a laminate-tube container according to the present invention can be markedly improved in the gas barrier property at the shoulder thereof. Accordingly, the quality of the contents of the container can be maintained for a long period of time and further, the quality assurance period by a manufacturer is greatly extended without releasing aroma or volatile components through the shoulder or causing any change in the quality of the contents.

Consequently, a laminate-tube container according to the present invention is greatly useful as the container to be used for toothpaste, medicine, food, drink, adhesive or the like.

Claims

1. A laminate-tube container having a shoulder improved in the barrier property, characterized in that the shoulder comprises a material composed of (A) 0 to 50% by weight of polyethylene, (B) 10 to 50 % by weight of an ethylene-vinyl alcohol copolymer or a saponified ethylene-vinyl acetate copolymer and (c) 10 to 90% by weight of a carboxylic acid-modified adhesive polyethylene resin.

FIG. 1




FIG. 2
PRIOR ART




FIG. 3
PRIOR ART

